

Tittle 172 pa Cerama. (Suarandi 1st)
 Glasur R76

Brandtemperatur:

Dato:

Ler:

Segeformel			Nr.	Syre tal
K ₂ O 0,149 CaO 0,551 Li ₂ O 0,3	Al ₂ O ₃ 0,5	SiO ₂ 3 B ₂ O ₃ 0,655	RL03/05/3	
K ₂ O 0,149 CaO 0,351 ZnO 0,3	Al ₂ O ₃ 0,6	SiO ₂ 3 B ₂ O ₃ 0,655	R203/06/3	
K ₂ O 0,149 CaO 0,851	Al ₂ O ₃ 0,6	SiO ₂ 3,2 B ₂ O ₃ 0,655	RW03/06/3	

Materiale	Nr. >	RL03/05/3	R203/06/3	RW03/06/32		
<u>R76</u> Tittle 172		74	71	70		
Harlin		15	21	9		
Harvts.		5	2			
Li ₂ CO ₃		6				
ZnO			7			
Willastonit				9		